



WANHAO STANDARD RESIN LIST REV.A

Technical Data

Ash	< 0.2%	Acidity	< 0.31mg KOH/g
Shore Hardness	75D	Water Content	< 0.23%
Experimental Shrink	3.3%	Surface Tension	36.5 Dynes/cm
Uncolored Reactivity	423mJ/cm ²	Tensile Strength	9100 PSI, 6% Elongation
Viscosity	@20 : 90CP	Glass Transition Temperature	104
Density	@25 :1.1g/cm ³	Packing	250ml/500ml/1000ml



CLEAR Part No. 0308060

Is our classic WANHAO Natural color. It's unpigmented resin, and is a clear color with light yellow. It's the go to resin color for thousands of 3D printers worldwide. Can't risk getting caught out here with a missed color choice? Go clear!



ORANGE Part No. 0308017

This is a new classic, one of the most blazon colors in the world. Safety orange! It's a bright traffic cone, safety vest orange and catches the eye any way you look at it.



YELLOW Part No. 0308064

This resin was custom suggested to our specifications and is a beautiful Yellow color. You know the yellow color of a banana? It's very close to that color!



WHITE Part No.0308058

White, like the driven snow. The possibilities are truly endless. This is a noticeably brighter shade than the Resin clear. With this new level of extreme brightness, you'll feel like you've been given a new lease on life. You'll have to wear shades.



GREEN Part No.0308061

This bright neon green wan hao Resin is custom suggested to us and ranks as our all time brightest color. Bright neon green, and even brighter and more popping under a UV or black light. Looks cool under blue LED stripes as well!



BLACK Part No. 0308059

Black A worldwide classic, this resin it's a particularly luxurious shade, think rich Swissmilk chocolate or decadent café au lait. Or something painted brown.



RED Part No.0308063

Transparent RED resin is an extremely awesome polymer for many reasons.



GRAY Part No.0308058

Bright Grey is one of fresh new color for 2017 it is bright than normal Grey.

SAFETY: For additional information please see the Material Safety Data Sheet.

STORAGE: Store in a tightly closed, opaque container in a properly vented storage area under dry conditions away from heat, sparks, and open flames. Shelf-life is 12 months from receipt.